



www.protectivepackaging.net

Certified: ISO 9001: 2015

PROTECT 200 MIL-PRF-131 Class I Data Sheet

**Super Heavy-Duty Barrier Packaging:
Watervaporproof, Greaseproof, Flexible, Heat-Sealable**

**Structure description: Biax Nylon/PE/Cross-Lam PE/PE/Foil/Heavy Duty
Coex**

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	10.3	mil	ASTM D2103
Puncture Resistance	40	lbs	FED STD 101
Tensile Strength	48	lbs/in	ASTM D882
Tear Strength	>1,000	grams	ASTM D1922
OTR	0.0005	cc/100 in ² /day @0% RH, 23°C	ASTM D3985
WVTR	0.0005	g/100 in ² /day @ 90% RH 40°C	ASTM F1249
Seal Strength	23	lbs/in	ASTM F88
Suggested Sealing Conditions	435°F, 60psi, 3.0sec		

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.