



www.protectivepackaging.net

Certified: ISO 9001: 2008

PROTECT MP 22 Light Duty Data Sheet

Greaseproof, Waterproof, Non-Corrosive, Moldable, and Self-Adhering

Marvel Pak 22 - Resistant to delamination due to extreme weather conditions. Marvel Pak 22 has wax on both sides.

Physical Properties

Typical Physical Test Results	Typical Values	TAPPI Test Method
Bursting Strength (Mullen)	30 lbs/in	TAPPI T103
Tear Resistance (MD & CD)	220 gms	TAPPI T114
Tensile Strength, lbs./in. (MD & CD)	12 /6 - # / in	TAPPI T494
Adhesion to Aluminum Panel	18 lbs	MIL-B-121f
Resistance to Heat & Humidity	No Delaminaiton	Exposed to 118F 65% RH 5 days

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.