

www.protectivepackaging.net Certified: ISO 9001: 2015

## PROTECT 2175 MIL-PRF-131 Class I Data Sheet

Structure: OPP/PE/Foil/PE

Meets all the requirements of **MIL-PRF-131K**, Class 1. Intended for applications requiring a flexible, heat-sealable barrier material with low MVTR. FR-2175 can be fabricated into pouches and used for protection of extremely critical items and materials. **DMF#14943** 

## **PHYSICAL PROPERTIES**

Property	Typical Value	Unit of Measure	Test Method
Caliper	5	mils	
Tensile (MD)	34	lbs at break	ASTM D-882
Tensile (CD)	29	lbs at break	ASTM D-882
Tear (MD)	64	grams	ASTM 689
Tear (XMD)	64	grams	ASTM 689
MVTR	0.0006	g/100sq in/24hrs	Mocon
O2TR	0.0006	g/100sq in/24hrs	Mocon
Puncture	15	lbs	FED TM2065
Seal Strength 375 °F: 26 psi: 1 sec	10	lbs/in	ASTM D-882

## Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.